

EUROGOM

ARTICOLO	GS 036/D	Norme di riferimento
COMPOSIZIONE	EPDM/SBR	
COLORE	NERO	
PESO SPECIFICO	1,5 gr/cm ³	ISO 2781 : 1998
DUREZZA SHORE A	60/65	ISO 7619 : 1986
CARICO DI ROTTURA	Mpa min.5	ISO 37 : 1994
ALLUNGAMENTO A ROTTURA	300%	ISO 37 : 1994
TEST OZONO (50pphm)	Nessuna Rottura	ASTM D 3395 a 40 °C
TEST A 100°C x 72 ore		durezza +10% carico di rottura +13% allungamento -45%
RESISTENZA ALLA LACERAZIONE	18 kn/m	ISO 34-1 : 1994
TEMPERATURA	- 40°C + 85°C	

Le informazioni sopra citate devono essere considerate come una guida ma non possono essere citate come un obbligo da parte nostra.

DATA SHEET

EUROFOAM

EUROGOM

ITEM	GS 036/D	Test Method
QUALITY	EPDM/SBR	
COLOUR	BLACK	
SPECIFIC GRAVITY	1,5 gr/cm3	ISO 2781 : 1998
SHORE HARDNESS	60/65	ISO 7619 : 1986
TEAR STRENGTH	Mpa min.5	ISO 37 : 1994
ELONGATION AT BREAK	300%	ISO 37 : 1994
TEAR RESISTANCE	18 kn/m	ISO 34-1 : 1994
OZONE TEST (50pphm)	NO CRACK	ASTM D 3395 at 40 °C
TEST AT 100°C x 72 hours		hardness +10% tensile strength +13% elongation -45%
TEMPERATURE	- 40°C + 85°C	
VERY GOOD RESISTANT TO OXIGEN	CHANGE VOLUME LESS THEN 10%	

The above given information should be considered as a guide but cannot regarded as an engagement from our side.